



SHREE EXTRUSIONS LIMITED

C26000

CARTRIDGE BRASS "70/30"

EQUIVALENT SPECIFICATIONS

SPECIFICATIONS	DESIGNATION
ISO	CuZn30
European	CuZn30
BS	CZ 106
JIS	C 2600
Russian	L70

C26000 has the highest ductility in the yellow brass series. Easily machined but is more often cold formed.

TYPICAL APPLICATIONS:

Architecture, Automotive, Builders Hardware, Consumer, Electrical, Fasteners, Industrial, Ordnance, Plumbing, Other

CHEMICAL COMPOSITION

	Cu	Fe	Pb	Zn
Min/Max	68.5 - 71.5	0.05	0.07	Rem
Nominals	70.0000	-	-	30.0000

PHYSICAL PROPERTIES

Coefficient of Thermal Expansion	11.1 μ • 10 ⁻⁶ per Δ °F (68-572 Δ °F)
Density	0.308 lb/in ³ @ 68 F
Electrical Conductivity	28 %IACS @ 68 F
Electrical Resistivity	37.0 ohms-cmil/ft @ 68 F
Melting Point Liquid US	1750 F
Melting Point Solid US	1680 F
Modulus of Elasticity in Tension	16000 ksi
Modulus of Rigidity	6000 ksi
Specific Gravity	8.53
Specific Heat Capacity	0.09 Btu/lb/ Δ °F @ 68 F
Thermal Conductivity	70.0 Btu Δ • ft/(hr Δ • ft ² Δ • Δ °F) @ 68 F

SIZES AVAILABLE :

WIRE	1mm To 8 mm
HOLLOW RODS	Min Bore Size 20 mm and Max OD 100 mm
ROUND RODS/BARS	6mm To 130 mm
HEX	5mm To 60mm
SQUARE	4mm To 60mm
FLAT	5mm Min Thickness and max Width 120mm
PROFILES / SECTIONS	AS per Customer Drawing
BILLETS	Up to 200 mm
INGOTS	As per Specification

Regd. Office & Works:
 217/218 Phase-II, Okha Rajkot Road, Dared, Jamnagar - 361 004. INDIA
 Tel.: +91 - 288 - 2730118 | Mobile: +91 - 9328105172
 mail@shree-extrusion.com | www.shree-extrusion.com



Quality, Technology & Vision at it's Best...